

**CLAIMS:**

1. A chemical vapor deposition method of forming a barium strontium titanate comprising dielectric layer, comprising:

positioning a substrate within a chemical vapor deposition reactor; and  
providing barium and strontium within the reactor by flowing at least one metal organic precursor to the reactor, and providing titanium within the reactor, and flowing at least one oxidizer to the reactor under conditions effective to deposit a barium strontium titanate comprising dielectric layer on the substrate, the oxidizer comprising H<sub>2</sub>O.

2. The method of claim 1 comprising flowing another inorganic oxidizer to the reactor during the deposit.

3. The method of claim 1 wherein the conditions comprise receipt of the substrate by a susceptor, the susceptor having a temperature of less than or equal to 550°C.

4. The method of claim 1 wherein the deposited layer is substantially homogeneous.

5. The method of claim 1 wherein the deposited layer is not substantially homogeneous.

6. A chemical vapor deposition method of forming a barium strontium titanate comprising dielectric layer, comprising:

positioning a substrate within a chemical vapor deposition reactor; and  
providing barium and strontium within the reactor by flowing at least one metal organic precursor to the reactor, and providing titanium within the reactor, and flowing at least one oxidizer to the reactor under conditions effective to deposit a barium strontium titanate comprising dielectric layer on the substrate, the oxidizer comprising  $H_2O_2$ .

7. The method of claim 6 comprising flowing another inorganic oxidizer to the reactor during the deposit.

8. The method of claim 6 wherein the conditions comprise receipt of the substrate by a susceptor, the susceptor having a temperature of less than or equal to  $550^{\circ}C$ .

9. The method of claim 6 wherein the deposited layer is substantially homogeneous.

10. The method of claim 6 wherein the deposited layer is not substantially homogeneous.

Sub  
A4

11. A chemical vapor deposition method of forming a barium strontium titanate comprising dielectric layer, comprising:

positioning a substrate within a chemical vapor deposition reactor; and  
providing barium and strontium within the reactor by flowing at least one metal organic precursor to the reactor, and providing titanium within the reactor, and flowing oxidizers to the reactor under conditions effective to deposit a barium strontium titanate comprising dielectric layer on the substrate, the oxidizers comprising at least  $H_2O$  and at least another oxidizer selected from the group consisting of  $O_2$ ,  $O_3$ ,  $NO_x$ ,  $N_2O$ , and  $H_2O_2$ , where "x" is at least 1.

12. The method of claim 11 wherein the another oxidizer comprises  $O_2$ .

13. The method of claim 11 wherein the another oxidizer comprises  $O_3$ .

Sub  
P1

14. The method of claim 11 wherein the another oxidizer comprises  $NO_x$ , where "x" is at least 1.

15. The method of claim 11 wherein the another oxidizer comprises  $N_2O$ .

16. The method of claim 11 wherein the another oxidizer comprises  $H_2O_2$ .

17. The method of claim 11 the oxidizers comprise at least two of the another oxidizers.

18. A chemical vapor deposition method of forming a barium strontium titanate comprising dielectric layer, comprising:

positioning a substrate within a chemical vapor deposition reactor; and providing barium and strontium within the reactor by flowing at least one metal organic precursor to the reactor, and providing titanium within the reactor, and flowing oxidizers to the reactor under conditions effective to deposit a barium strontium titanate comprising dielectric layer on the substrate, the oxidizers comprising at least  $H_2O_2$  and at least another oxidizer selected from the group consisting of  $O_2$ ,  $O_3$ ,  $NO_x$ , and  $N_2O$ , where "x" is at least 1.

19. The method of claim 18 wherein the another oxidizer comprises  $O_2$ .

20. The method of claim 18 wherein the another oxidizer comprises  $O_3$ .

21. The method of claim 18 wherein the another oxidizer comprises  $\text{NO}_x$ , where "x" is at least 1.

22. The method of claim 18 wherein the another oxidizer comprises  $\text{N}_2\text{O}$ .

23. The method of claim 18 wherein the another oxidizer comprises  $\text{H}_2\text{O}_2$ .

24. The method of claim 18 the oxidizers comprise at least two of the another oxidizers.